

Redi-Plug is a pre-packaged, fast-setting, concrete repair mortar containing industrial hydraulic cements. It is designed to set within 30 seconds under normal job-site conditions.

FEATURES & BENEFITS

- Sets within 30 seconds
- Easy to use; just add water
- Non-metallic and does not contain calcium chlorides, plasters or gypsum
- Superior bond; will not wash-out
- Durable to hot or cold temperatures
- Colour similar to concrete grey
- Reaches 24 MPa in 24 hours
- All KING products are manufactured using ISO 9001:2015 Certified Processes

USES

- Repairs leaks in concrete sewer pipes, manholes, catch basins, tanks or any other concrete or masonry surfaces

PROCEDURES

Surface Preparation: All surfaces to be in contact with Redi-Plug must be free from dust, oil, grease or any other foreign substances that may interfere with the bond of the material. Remove all delaminated or unsound concrete providing a roughened surface. Cracks or breaks in the concrete should be chiseled out in the shape of a "U" deeper than wider. Clean the area to be repaired with potable water, leaving the concrete saturated but free of standing water (SSD).

Mixing: In a disposable plastic pail, place approximately 1 part potable water followed by 3 to 3.5 parts of Redi-Plug. This is an approximate ratio. Therefore, it is recommended that you add sufficient water to form a solid ball. Mix quickly and thoroughly with a trowel.

Placing: Once pliable, form into a ball and pack into the repair area without delay. Hold in place for 1 to 2 minutes, to ensure that full bond has taken place. Mix only what can be placed within a 10 to 15 second time limit, as the product will start to harden, especially in warm temperatures.

CURING

Curing is essential to optimize physical properties of Redi-Plug and minimize plastic shrinkage. Redi-Plug should be cured immediately after material has reached initial set in accordance with ACI 308 "Guide to Curing Concrete". Continuously moist cure for a minimum period of 7 days. Alternatively, moist cure for a minimum period of 24 hours and apply a curing compound that complies with ASTM C 309.

TECHNICAL DATA

The following data is representative of typical values achievable under laboratory conditions. Results in the field may vary.

MIXING RATIO

1:3

COMPRESSIVE STRENGTH

ASTM C 109

6 Hour	16 MPa (2320 psi)
1 Day	24 MPa (3480 psi)
3 Day	32 MPa (4640 psi)
7 Day	40 MPa (5800 psi)
28 Day	45 MPa (6525 psi)

OPTIMUM PERFORMANCE

Higher temperatures will accelerate the setting time and cooler temperatures will retard the setting time. Therefore, Redi-Plug is not recommended in temperatures below 10 °C (50 °F). For concrete repairs that are under water, use Duro-Crete UW, which is specially designed for underwater applications.

YIELD

20 KG (44 lb) pail contains approximately 0.013 m³ (0.46 ft³).

PACKAGING

Redi-Plug is normally packaged in 20 KG (44 lb) industrial plastic pails with a sealed tear-tab lids, and polywrapped on wooden pallets. All KING products can be custom packaged to suit specific job requirements.

STORAGE AND SHELF LIFE

Material should be stored in a dry, covered area, protected from the elements. Unopened pails have a shelf life of 12 months.

SAFETY PROCEDURES

Redi-Plug contains hydraulic cements. Normal safety-wear such as rubber gloves, dust mask and safety glasses used to handle conventional cement based products should be worn. Safety Data Sheets are available upon request.

Warranty: This product is designed to meet the performance specifications outlined in this product data sheet. If the product is used in conditions for which it was not intended, or applied in a manner contrary to the written recommendations contained in the product data sheet, the product may not reach such performance specifications. The foregoing is in lieu of any other warranties, representations or conditions, expressed or implied, including, but not limited to, implied warranties or conditions of merchantable quality or fitness for particular purposes, and those arising by statute or otherwise in law or from a course of dealing or usage of trade. [REV.0005_2458717.5]

Oakville Office
555 Michigan Drive, Suite 100,
Oakville, ON
L6L 0G4

Montreal Office & Plant
3825 rue Alfred-Laliberté,
Boisbriand, QC
J7H 1P7

Brantford Office & Plant
541 Oak Park Road,
Brantford, ON
N3T 5L8

Sudbury Office & Plant
644 Simmons Road,
Dowling, ON
P0M 1R0